CNCGLASS

CNCGLASS nylon PA6 peel ply (white woven roll with red tracer lines) — product photo, watermarked.

CNCGLASS Product Catalog

Peel Ply 190 °C — Nylon PA6 Release Fabric for Vacuum Bagging

English

Nylon PA6 peel ply / release fabric for vacuum infusion, wet lay-up, and vacuum precompaction vacuum-bag processes — white with red tracer lines, rated to 190 °C.

CNCGLASS | www.cncglass.com

Product List Edition

CNC Ucolin Interlayer Technology Co., Ltd. · SHENZHEN, GD, CHINA

CNCGLASS · Product List / Specifications

Nylon PA6 peel ply / release fabric. Nylon yarn woven, washed and heat-set. Red tracer lines equally spaced — visible before and after cure to prevent leave-in residue. After peel, the surface needs less or no sanding for secondary bonding. Low cost for vacuum process. For vacuum infusion, wet lay-up, and vacuum precompaction vacuum-bag processes; good release. Width 1–2 m; length 100–200 m. Material: nylon PA6; 88 g/m²; thickness 0.152 mm; service temperature 190 °C; white with red tracer lines. Custom width and length available. Distinct nylon PA6 grade (not polyester).

Specifications below. Commercial terms available on request.

Product	Specifications	Packing	Application
Peel Ply 190 °C (Nylon PA6)	88 g/m² · 0.152 mm · width 1–2 m	100–200 m/roll	Vacuum infusion / wet lay-up / precompaction

Note: White with red tracer lines. Custom width / length available. Please contact us for commercial terms.

To place an order or request a quotation, please email us at cnc@cncGlass.com. Our sales team will respond promptly with availability and lead time.

CNCGLASS · Datasheet of Peel Ply 190 °C

Key properties of CNCGLASS nylon PA6 peel ply / release fabric for vacuum infusion, wet lay-up, and vacuum precompaction. Values below are published product facts for reference. Nylon PA6 grade — distinct from polyester peel ply.

Property	Result	Note
Material	Nylon PA6	Product fact — not polyester
Yarn / finish	Nylon yarn woven, washed and heat-set	Product fact
Weight	88 g/m²	Product fact
Thickness	0.152 mm	Product fact
Service temperature	190 °C	Maximum service
Color	White with red tracer lines	Equally spaced tracers
Tracer lines	Visible before and after cure	Prevent leave-in residue
Release	Good release	Easy peel after cure
Finish after peel	Less / no sanding for secondary bonding	Product fact
Process cost	Low cost for vacuum process	Product fact
Width	1–2 m	Standard range
Length	100–200 m	Per roll
Customization	Width / length on request	Custom available

Datasheet values are typical published facts and may vary by batch. Please contact us for the latest test reports.

CNCGLASS · Storage

Store in a ventilated, dry, clean warehouse. Stack neatly; do not crush, deform, or damage the rolls. Keep at least 2 m from any heat source. Shelf life ≤ 2 years.

CNCGLASS · How It Works (Hand-Drawn Sketches)

Educational hand-drawn sketches for glaziers and composite shops. Nylon PA6 peel ply is placed against the laminate in the vacuum bag stack. Red tracer lines remain visible before and after cure so leave-in residue is avoided. After peel, less or no sanding is needed for secondary bonding. Suitable for vacuum infusion, wet lay-up, and vacuum precompaction vacuum-bag processes (service temperature 190 °C). Nylon PA6 grade — distinct from polyester peel ply.



Vacuum bag stack (hand-drawn sketch): Nylon PA6 peel ply on the laminate under release film / breather / bag — nylon PA6 grade for service up to 190 °C (distinct from polyester peel ply).



Red tracer lines (hand-drawn sketch): equally spaced tracers visible before and after cure prevent leave-in residue; after peel, less or no sanding for secondary bonding — Nylon PA6, 190 °C.



Applications (hand-drawn sketch): vacuum infusion, wet lay-up, and vacuum precompaction / vacuum-bag processes — Nylon PA6 peel ply release fabric at 190 °C.

CNCGLASS · Product Photos

Product photographs of CNCGLASS nylon PA6 peel ply (watermarked). One product photo from the linked page; close-up cropped from the same roll. White woven fabric with red tracer lines.



Nylon PA6 peel ply roll with red tracer lines

Nylon PA6 weave close-up (same roll)

CNCGLASS · Contact

CNC Ucolin Interlayer Technology Co., Ltd.

Address: SHENZHEN, GD, CHINA

Peter Lin

Email: cnc@cncGlass.com

WhatsApp / Mobile: +86 15013829504

WeChat: wecan365

Website: www.cncglass.com

For quotations, samples, or bulk orders of nylon PA6 peel ply / release fabric for vacuum infusion, wet lay-up, and vacuum precompaction, please contact us by email or WhatsApp.

CNCGLASS · Peel Ply 190 ℃ — Nylon PA6 Release Fabric